

Wellcoat Epoxy Textotile

<p>A solvent borne two pack epoxy intermediate spray coat for Epoxy Textotile system. The product is convertible to various texture form & is supposed to be overcoated with Wellcoat Superthane topcoat to form Epoxy Textotile system. The system exhibits outstanding exterior durability with good anti-carbonation property.</p>	<p>PRODUCT</p>
<ul style="list-style-type: none"> • Exceptional outdoor durability • Excellent dirt pickup resistance • Excellent chemical, mechanical & abrasion resistance. • Available in several shades 	<p>FEATURES</p>
<p>Intermediate coat for Epoxy Textotile system.</p> <p>Area of Use : Interior and Exterior</p> <p>Substrate : Ideal for concrete, plaster, brick work & block work.</p>	<p>RECOMMENDED USE</p>
<p>Color : White/Off-white & select shades</p> <p>Finish : Matt</p> <p>NVM% : 66-70</p> <p>Thinner/Cleaner : Epoxy Thinner WT-4</p> <p>Thinning volume : 5-7% max</p> <p>Mixing Ratio : 4:1 (Base: Hardner)</p> <p>Typical DFT : 200-300 microns</p> <p>Pot Life : 6-8 hrs</p> <p>Theoretical coverage : 2 to 3 m²/lt</p> <p>Practical coverage : Would depend on surface quality, application skill, loss due to handling etc.</p> <p>Drying time @ 30°C : Touch dry – 4 hrs</p> <p>Recoating time :15 hrs</p> <p>Pack size : 1USG,5USG</p>	<p>SPECIFICATION & OTHER INFORMATION</p>

<p>The product is applied by a special hopper spray gun with higher orifice diameter (6-8mm) at 70-80 psi. Ensure adequate ventilation during spray & drying of the film & humidity during application doesn't exceed 95%.</p>	<p>APPLICATION METHOD</p>
<p>After ensuring that surface is clean, dry & free of organic contaminants apply Epoxy Textotile system: Wellcoat Acrylic primer (1 coat) + Epoxy Textotile system (1 coat) + Wellcoat Superthane (2 coats)</p>	<p>SURFACE PREPARATION & SYSTEM</p>
<p>Storage & Disposal : Store under cool & dry condition with adequate ventilation. Dispose in land fill as per guidance of statutory authority Don't empty the cans in drains, sewers or other water courses. Flash point : 25°C Shelf life : 12 months in closed condition</p>	<p>STORAGE & HANDLING</p>
<ul style="list-style-type: none"> • Avoid contact with the skin and eyes. Wear protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. • Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour or spray. • In case of accidental splashes wash the eyes with water & skin with mild soap & water. Never use solvent for cleaning body. • In case of inhalation & ingestion expose the person to fresh air & finally consult doctor as quickly as possible, Don't induce vomiting. ▪ For details on Safety & Handling refer to MSDS. 	<p>SAFETY PRECAUTIONS & FIRST AID</p>
<p>The Product information sheet is meant for general information of the product. Optimal performance by the product would be achieved on correct selection of paint & painting system, proper surface preparation & application. Unless specifically agreed in writing by us we won't be responsible for 100% performance of the product. Product information sheet would be subject to modification as & when product is modified/improved. Our endeavor would be to keep you abreast of change.</p>	<p>DISCLAIMER</p>