

MAXIWOOD N.C PIGMENTED TOPCOAT

<p>A quick drying nitrocellulose based pigmented topcoat for wooden substrates. The product is more suitable for interior application. It's fast drying property enhances productivity by quick turnaround time. The product is available in gloss, matt & silk-matt version.</p> <p>Another variant of this product for application over metal substrate for Auto repair system is also available.</p>	<p>PRODUCT</p>																														
<p>Quick drying with fast turnaround time & less dirt pick up.</p> <p>Wood version is more suitable for interior, but metal version can be used interior & exterior.</p> <p>Economic & easy to apply</p> <p>Available in high gloss & polishable variety.</p>	<p>FEATURES</p>																														
<p>Natural wood & wood substitutes like fibre board, veneer etc. More suitable for interior use</p>	<p>RECOMMENDED USE</p>																														
<table border="0"> <tr> <td>Finish</td> <td>: Smooth , glossy, matt & silk-matt version</td> </tr> <tr> <td>NVM%</td> <td>: Gloss - 40-45 , Matt/Silk-matt -42-48% (Depending on Shade)</td> </tr> <tr> <td>Gloss at 60 degree</td> <td>:Gloss finish 78-82%, Matt & Silk-matt 10-15% & 35-40% respectively.</td> </tr> <tr> <td>Supply viscosity</td> <td>: 115-125 KU at 30^o C</td> </tr> <tr> <td>Thinner</td> <td>:NC Thinner WT-33/ WT-2/ WT-1A</td> </tr> <tr> <td>Thinning Ratio (vol)</td> <td>: 1:1</td> </tr> <tr> <td>Method of application</td> <td>: Conventional spray , Brush (over a small area)</td> </tr> <tr> <td>Shades</td> <td>: As per company shade card</td> </tr> <tr> <td>Theoretical coverage</td> <td>: 7-8 m2/lt at 30 micron DFT</td> </tr> <tr> <td>Practical coverage</td> <td>: would depend on the surface profile, application skill & method, loss in the container.</td> </tr> <tr> <td>Drying time (@30°C)</td> <td>: Surface dry 10-12 minutes</td> </tr> <tr> <td>Sandable dry</td> <td>:1 hr @30°C</td> </tr> <tr> <td>Hard dry</td> <td>: 3-4 hrs @30°C</td> </tr> <tr> <td>Stackable dry</td> <td>: 4 hrs @30°C</td> </tr> <tr> <td>Pack size</td> <td>: 1USG,5USG</td> </tr> </table>	Finish	: Smooth , glossy, matt & silk-matt version	NVM%	: Gloss - 40-45 , Matt/Silk-matt -42-48% (Depending on Shade)	Gloss at 60 degree	:Gloss finish 78-82%, Matt & Silk-matt 10-15% & 35-40% respectively.	Supply viscosity	: 115-125 KU at 30 ^o C	Thinner	:NC Thinner WT-33/ WT-2/ WT-1A	Thinning Ratio (vol)	: 1:1	Method of application	: Conventional spray , Brush (over a small area)	Shades	: As per company shade card	Theoretical coverage	: 7-8 m2/lt at 30 micron DFT	Practical coverage	: would depend on the surface profile, application skill & method, loss in the container.	Drying time (@30°C)	: Surface dry 10-12 minutes	Sandable dry	:1 hr @30°C	Hard dry	: 3-4 hrs @30°C	Stackable dry	: 4 hrs @30°C	Pack size	: 1USG,5USG	<p>SPECIFICATION & OTHER INFORMATION</p>
Finish	: Smooth , glossy, matt & silk-matt version																														
NVM%	: Gloss - 40-45 , Matt/Silk-matt -42-48% (Depending on Shade)																														
Gloss at 60 degree	:Gloss finish 78-82%, Matt & Silk-matt 10-15% & 35-40% respectively.																														
Supply viscosity	: 115-125 KU at 30 ^o C																														
Thinner	:NC Thinner WT-33/ WT-2/ WT-1A																														
Thinning Ratio (vol)	: 1:1																														
Method of application	: Conventional spray , Brush (over a small area)																														
Shades	: As per company shade card																														
Theoretical coverage	: 7-8 m2/lt at 30 micron DFT																														
Practical coverage	: would depend on the surface profile, application skill & method, loss in the container.																														
Drying time (@30°C)	: Surface dry 10-12 minutes																														
Sandable dry	:1 hr @30°C																														
Hard dry	: 3-4 hrs @30°C																														
Stackable dry	: 4 hrs @30°C																														
Pack size	: 1USG,5USG																														

<p>The product is best applied by conventional spray although application by brush is possible over a small area. Avoid brush application over a large surface area. Ensure wood is dry, clean & free from contaminants. Sand the surface with a coarse (P180) followed by fine sand paper (P 400) along the direction of grains. Dust off the surface & apply a coat of Maxiwood filler if required. Allow it to dry for 1 hr & sand off the excess filler & clean the surface. Apply a coat of Maxiwood N.C primer surfacer after thinning with NC thinner. Allow it to dry for one & half hour, flat the surface using P400 Emery paper, dust off & apply two coats of Maxiwood N.C pigmented top coat after thinning with NC thinner.</p>	SURFACE PREPARATION & APPLICATION
---	--

<p>Storage & Disposal Store in cool, dry condition keeping container tightly closed in accordance with petroleum (mixture) order, SRO 1929 No 993. & dispose by controlled land fill as per requirement of statutory authority. Don't empty into drains, sewers or other water courses.</p> <p>Flash Point : Below 20^oC, Highly flammable. Shelf Life : Upto 12 months in closed condition</p>	STORAGE & HANDLING
---	-----------------------------------

<ul style="list-style-type: none"> ▪ Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. ▪ Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapor or spray. ▪ This product is flammable. Keep away from sources of ignition. Do not smoke. Take precautionary measures against static discharge. In case of fire, blanket flames with foam, carbon-dioxide or dry chemicals. ▪ Eyes & Skin: In the event of accidental splashes, flush eyes with warm water & wash skin with mild soap and seek quick medical advice. Never use solvent for cleaning the affected areas. ▪ Inhalation & Ingestion: Remove to fresh air, loosen collar. Don't induce vomiting. 	SAFETY PRECAUTIONS & FIRST AID
--	---

<p>The product information sheet is meant for general information of the product. Optimal performance by the product would be achieved on correct selection of paint & painting system, proper surface preparation & application. Unless specifically agreed in writing by us we won't be responsible for 100% performance of the product. Product information sheet would be subject to modification as & when product is modified/improved. Our endeavor would be to keep you abreast of change.</p>	DISCLAIMER
--	-------------------