

MAXIWOOD N.C SANDING SEALER

<p>A very quick drying nitrocellulose based single pack sanding sealer designed for use over wood & wood substitutes like fibre board, veneer, particle board before application of topcoat. Main role of Maxiwood sanding sealer is to guard against dimensional distortion of wooden substrate as well as serving as barrier coat between bare wood & topcoat to provide best performance & finish. It fills wood grain without disturbing its natural look.</p>	<p>PRODUCT</p>																						
<ul style="list-style-type: none"> • Very quick drying hence higher productivity & less dirt pick-up • Excellent sanding property • Can be used as filler cum sanding sealer if surface imperfection is insignificant. • Works for interior & exterior. 	<p>FEATURES</p>																						
<p>Natural wood & wood substitutes like fibre board, veneer etc. Suitable for interior & exterior use.</p>	<p>RECOMMENDED USE</p>																						
<table> <tr> <td>Finish</td> <td>: Smooth, Matt</td> </tr> <tr> <td>NVM %</td> <td>: 36-38</td> </tr> <tr> <td>Supply viscosity</td> <td>: 115-125 KU at 30°C</td> </tr> <tr> <td>Thinner</td> <td>: NC Thinner WT-1/WT-1A/WT-33</td> </tr> <tr> <td>Thinning Ratio (vol)</td> <td>: 1:1.5</td> </tr> <tr> <td>Application</td> <td>: Coventional spray</td> </tr> <tr> <td>Theoretical coverage</td> <td>: 9 m²/Ltr at 25micron DFT</td> </tr> <tr> <td>Practical coverage</td> <td>: Would depend on surface profile, Application method & Skill & loss in the container</td> </tr> <tr> <td>Drying (300C)</td> <td>: Sandable dry 35 - 45 minutes</td> </tr> <tr> <td>Overcoating time</td> <td>: One & half hour</td> </tr> <tr> <td>Pack size</td> <td>: 1USG,5USG</td> </tr> </table>	Finish	: Smooth, Matt	NVM %	: 36-38	Supply viscosity	: 115-125 KU at 30°C	Thinner	: NC Thinner WT-1/WT-1A/WT-33	Thinning Ratio (vol)	: 1:1.5	Application	: Coventional spray	Theoretical coverage	: 9 m ² /Ltr at 25micron DFT	Practical coverage	: Would depend on surface profile, Application method & Skill & loss in the container	Drying (300C)	: Sandable dry 35 - 45 minutes	Overcoating time	: One & half hour	Pack size	: 1USG,5USG	<p>SPECIFICATION & OTHER INFORMATION</p>
Finish	: Smooth, Matt																						
NVM %	: 36-38																						
Supply viscosity	: 115-125 KU at 30°C																						
Thinner	: NC Thinner WT-1/WT-1A/WT-33																						
Thinning Ratio (vol)	: 1:1.5																						
Application	: Coventional spray																						
Theoretical coverage	: 9 m ² /Ltr at 25micron DFT																						
Practical coverage	: Would depend on surface profile, Application method & Skill & loss in the container																						
Drying (300C)	: Sandable dry 35 - 45 minutes																						
Overcoating time	: One & half hour																						
Pack size	: 1USG,5USG																						

<p>The product is best applied by conventional spray at viscosity of 20-22 sec/30°C & pressure 40-45 psi.</p> <p>Ensure wood is dry, clean & free from contaminants. Sand the surface with a coarse (P180) followed by fine sand paper (P400) along the direction of grains. Dust off the surface & apply a coat of Maxiwood filler if grain filling is required. Allow it to dry for 1 hr & sand off the excess filler & clean the surface. Apply a coat of Maxiwood N.C sanding sealer after thinning with Wellcoat NC thinner. Allow it to dry for 45 minutes. Sand off with P400 & clean the surface before application of topcoat. If the wood surface has lots of imperfection Maxiwood filler is advised to be used as first coat followed by Maxiwood sanding sealer. For minor imperfection the product can be directly used with satisfactory performance.</p> <p>Do not use filler if grain filling is not required. Avoid application of NC products under high humidity to avoid blooming. Also, NC products are not advised over enamel. It would lead to lifting of the underneath coat.</p>	<p>SURFACE PREPARATION & APPLICATION</p>
---	---

<p>Storage & Disposal Store in cool, dry condition keeping container tightly closed in accordance with petroleum (mixture) order, SRO 1929 No 993. & dispose by controlled land fill as per requirement of statutory authority. Don't empty into drains, sewers or other water courses.</p> <p>Flash Point : Below 20°C, Highly flammable.</p> <p>Shelf Life : Upto 12 months in closed condition</p>	<p>STORAGE & HANDLING</p>
---	--

<ul style="list-style-type: none"> ▪ Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream. ▪ Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapor or spray. ▪ This product is flammable. Keep away from sources of ignition. Do not smoke. Take precautionary measures against static discharge. In case of fire, blanket flames with foam, carbon-dioxide or dry chemicals. ▪ Eyes & Skin: In the event of accidental splashes, flush eyes with warm water & wash skin with mild soap and seek quick medical advice. Never use solvent for cleaning the affected areas. ▪ Inhalation & Ingestion: Remove to fresh air, loosen collar. Don't induce vomiting. 	<p>SAFETY PRECAUTIONS & FIRST AID</p>
--	--

<p>The product information sheet is meant for general information of the product. Optimal performance by the product would be achieved on correct selection of paint & painting system, proper surface, surface preparation & application. Wellcoat Paints warranty product quality only. Product information sheet would be subject to modification as & when product is modified/improved. Our endeavor would be to keep you abreast of change.</p>	<p>DISCLAIMER</p>
---	--------------------------